



FLUID ANALYSIS

UIN 08E546F

Final Drive

Unit No. 1DW772GPVKF695391

Unit:
Make John Deere
Model 772GP
Serial No. 1DW772GPVKF695391

Site

Compartment:

Name Right Final Drive
Make
Model
Serial No.
Capacity: Ltrs

Customer:

DIAGNOSIS

Oil type and/or fluid grade not given. No abnormal wear detected. No recommended action at this time. Resample at normal intervals. Time on oil not provided with sample.

ANALYST: Pat.Libutti

LEGEND				
Normal	Severe	Abnormal	Caution	Normal

DATE SAMPLED	04-Oct-21
DATE RECEIVED	06-Oct-21
DATE REPORTED	07-Oct-21

LAB NO.		40210527723
SIF NO.		39304798
TIME ON UNIT	Hrs	2412
TIME ON OIL	Hrs	
OIL BRAND		Unidentified
OIL TYPE		Unidentified
OIL GRADE		Unknown
OIL ADDED		
FILTER		Not Applicable
OIL CHANGED		Not Changed
WO NUMBER		1629085

Metals (ppm)

Iron (Fe)	76
Chromium (Cr)	<1
Lead (Pb)	<1
Copper (Cu)	<1
Tin (Sn)	<1
Aluminium (Al)	4
Nickel (Ni)	<1
Silver (Ag)	<1
Titanium (Ti)	<1
Vanadium (V)	<1

Contaminants (ppm)

Silicon (Si)	10
Sodium (Na)	4
Potassium (K)	1
Water (%)	<0.05
Solids (%)	1.0

Additives (ppm)

Magnesium (Mg)	125
Calcium (Ca)	4012
Barium (Ba)	<1
Phosphorus (P)	1201
Zinc (Zn)	1466
Molybdenum (Mo)	<1
Boron (B)	7

Physical Tests

Viscosity (cSt 40C)	60.7
---------------------	------

Physical / Chemical

Acid Number (mgKOH/g)	2.47
-----------------------	------

Additional






PQ Index	231
----------	-----





FLUID ANALYSIS

UIN 08E546F



Filter Image

Filter patch test is not performed Contact laboratory for more information

U.S. Laboratories

Atlanta, Georgia - 420
5300 OakBrook Parkway
Building 200 Suite 245
Norcross, GA 30093
800.394.3669

Valley View, Ohio - 410
6180 Halle Dr. Suite D
Valley View, OH 44125
800.726.5400

Kansas City, Kansas - 430
935 Sunshine Road
Kansas City, KS 66115
800.332.8055

Phoenix, Arizona - 440
3319 West Earll Drive
Phoenix, AZ 85017
800.445.7930

Portland, Oregon - 401
4943 NW Front Avenue
Portland, OR 97210
800.770.4128

Canadian Laboratories

Burlington, Ontario - 450
5036 South Service Rd.
Burlington, ON L7L5Y7
905.332.9559

Edmonton, Alberta - 402
9450 17 Ave NW
Edmonton, AB T6N 1M9
888.489.0057

Sales & Marketing

Houston, Texas
10450 Stancliff Road, Suite 210
Houston, TX 77099
877.835.8437

International Locations

Australia
Brisbane, Perth, Sydney, Muswellbrook

South America
Santiago de Chile, Belo Horizonte, Brazil

New Zealand
Wellington

Southeast Asia
Kuala Lumpur, Singapore

Europe
Prague

TEST METHODS:

Acid Number: ASTM D974/D664 (*M)
Base Number: ASTM D4739 (*M)
Base Number (Perchloric): ASTM D2896 (*M)
Fuel Dilution by GC: ASTM D7593
Fuel Dilution Visc/Setaflash In House
Fuel Soot ATR/IR: ASTM D7686 (*M)
Soot by FTIR: ASTM D7844
Glycol: In House
Metals by ICP AES: ASTM D5185 (*M)
Ox, NOx, SOx, FTIR: ASTM E2412/D7418/D7414 D7415
PQ Index: ASTM D8120 (*M)
Particle Count: ASTM D7647 (*M) / ISO 4406
Viscosity: ASTM D445 (*M) / D7279 (*M)
Water KF: D6304 / E203 (*M)
Water Crackle: In House

*M - Modified Method

Since services are based on samples and information supplied by others, and since corrective actions, if any, are necessarily taken by others, these services are rendered without any warranty or liability of any kind beyond the actual amount paid to ALS Tribology for the services. Reported recommendations are based on interpretations of the generated test results and historical data. Certain test results appearing in this report may have been tested at other ALS laboratories within the Tribology divisional network.

